



**I-Minerals Inc.**



**Typical Analysis** DEVELOPMENTAL PRODUCT

**TrueQ<sup>®</sup> 3-50**

% retained (incremental)		
mesh	μ	TrueQ 1-325
50	300	0.1
70	212	33.2
100	150	49.9
140	106	15.1
200	75	1.7
Thru		tr
Apparent Loose Bulk Density (lb/ft <sup>3</sup> )		84

**TrueQ<sup>®</sup>3 I-Minerals Analysis by Lot %**

	Al <sub>2</sub> O <sub>3</sub>	CaO	Fe <sub>2</sub> O <sub>3</sub>	K <sub>2</sub> O	MgO	TiO <sub>2</sub>	SiO <sub>2</sub>
<b>TrueQ 3</b>	0.038	0.001	0.004	0.006	0.001	0.002	99.97

**TrueQ<sup>®</sup>3 I-Minerals Analysis, by Lot, ppm wt.**

	Al	Ca	Cu	Fe	K	Li	Mg	Mn	Na	Ti
<b>TrueQ 3</b>	200	10	0.5	30	50	2	5	2	20	15

05.23.2017

For More Info: Linda Koep | [Lkoep@imineralsinc.com](mailto:Lkoep@imineralsinc.com) | 208-659-8787

The information and data contained herein are believed to be accurate, but the manufacturer makes no warranty with respect thereto and disclaims responsibility for reliance thereon. These data relate only to the specific material described herein, and does not relate to use in connection with any other materials or in any process.

I-Minerals Inc. makes no warranties, express or implied, concerning this product. No warranty of fitness for any particular purpose is made and we assume no responsibility whatever for any use of this product. This product should be used by properly trained personnel, and in compliance with applicable health and safety laws and regulations.